

CLIPPEDIMAGE= JP02001077471A
PAT-NO: JP02001077471A
DOCUMENT-IDENTIFIER: JP 2001077471 A
TITLE: SEMICONDCUTOR LASER

PUBN-DATE: March 23, 2001

INVENTOR-INFORMATION:

NAME	COUNTRY
AKASAKI, ISAMU	N/A
AMANO, HIROSHI	
KAMIYAMA, SATOSHI	N/A
IWATANI, MOTOAKI	
	N/A
	N/A

ASSIGNEE-INFORMATION:

NAME	COUNTRY
JAPAN SCIENCE & TECHNOLOGY CORP	N/A

APPL-NO: JP11248038

APPL-DATE: September 1, 1999

INT-CL_(IPC): H01S005/223; H01L033/00

ABSTRACT:

PROBLEM TO BE SOLVED: To suppress generation of cracks due to lattice mismatching, existing between a current constricting layer and an n-type layer by a method, where an AlGaInN layer is deposited from the place separated further than by a specified distance from the contact surface of a substrate with a buffer layer at the film-forming temperature in a specific range between p-type electrodes.

SOLUTION: An AlN buffer layer 2, an n-type GaN layer 3, a low- temperature AlGaN intermediate layer 4 and an AlGaInN current constricting layer 5, deposited at a film-forming temperature of 300 to 800

COPYRIGHT: (C)2001,JPO